



News & Views

All-inorganic perovskite nanocrystal materials: new generation of scintillators for high quality X-ray imaging

Kang Wang^a, Hao Zhang^{a,*}, Zhanjun Gu^b^a Aerospace Institute of Advanced Materials & Processing Technology, Beijing 100074, China^b CAS Key Laboratory for Biomedical Effects of Nanomaterials and Nanosafety, Institute of High Energy Physics and National Center for Nanoscience and Technology of China, Chinese Academy of Sciences, Beijing 100049, China

Scintillating materials, which can convert high energy X-ray radiation into visible luminescence [1], are crucial parts of X-ray imaging technology. Since the discovery of X-ray in 1895, scintillating materials have witnessed wide applications in various fields, including security inspection, space exploration, non-destructive detection, and medical diagnostics [2,3]. Conventional scintillators are generally large inorganic crystals and can only be grown at high temperature, which significantly increases the manufacturing difficulty and cost. The luminescence of current crystal scintillators is usually limited by low-efficiency or afterglow effects, and is difficult to be tuned across the visible spectrum. As traditional scintillators have reached their performance limits, exploration of new scintillators has become a crucial topic considering the increased demands of X-ray imaging and detection technology [4–6].

To solve the limitations of conventional scintillator materials, Liu and co-workers [7] have recently reported a revolutionary discovery of novel scintillators based on all-inorganic CsPbX₃ (X = Cl, Br or I) perovskite nanocrystals, with the ability of converting small dose of X-ray radiation into intensive and multi-color visible luminescence (Fig. 1). Their discovery might open up new opportunities for advancing the X-ray imaging technology.

A series of cubic CsPbX₃ perovskite nanocrystals (CsPbX₃ PNCs) were prepared through a hot-injection method, which could exhibit color-tunable X-ray-excited luminescence by tailoring the halogen components, providing opportunities for multi-color X-ray visualization. The luminescence intensity of CsPbBr₃ PNCs is comparable to high-efficiency CsI:Tl⁺ crystal scintillators and surpasses most of conventional bulky scintillators. Such intensive luminescence ability can be attributed to the quantum confinement effects [8], which increase the recombination rate of charge carriers and create discrete emission energy levels. The strong radiation stopping power of heavy Pb-atom as well as highly emissive triplet excited states also contribute to the high efficiency emission.

Besides the advantages of intensive and color-tunable luminescence, CsPbBr₃ PNCs are also featured with other excellent scintillating properties to deliver rapid, ultrasensitive and low-radiation-risk X-ray imaging technology. The scintillator film based on CsPbBr₃ PNCs exhibits lowest detectable dose rate of 13 nGy s^{−1}, which is more than 400 times lower than typical doses for X-ray diagnostics. The scintillator film also has a fast response time of 44.6 ns without afterglow effect, providing great opportunities for real-time X-ray imaging. The fast response and low detectable dose limit are also crucial to reduce the irradiation exposure in medical radiography. Additionally, the scintillator film allows convenient record of X-ray images using common digital cameras, offering promising chances for electronic inspection and biologic imaging. The flat-panel X-ray detector based on CsPbBr₃ PNCs is able to image internal structures of electronic circuit boards and smart phones with good spatial resolution. Thus, the breakthrough of Liu and co-workers surely provided a new generation of scintillator material which could light the way to high-resolution, low-cost and ultrasensitive X-ray imaging technology.

Since the revolutionary discovery of novel nanocrystal scintillators by Liu and co-workers, advances of CsPbBr₃ PNCs based scintillators have been made in the last year. Im and co-workers [9] developed a CsPbBr₃ PNCs based X-ray detector with high-performance scintillating abilities. Zhang et al. [10] reported the scintillating properties of easily accessible CsPbBr₃ nanosheets colloidal and solid film scintillators. The self-assembly of CsPbBr₃ nanosheets can offer convenient access to high-quality and large-area CsPbBr₃ solid film with intensive radioluminescence, fast response time, long-term radiostability and good spatial resolution, providing potential approach to high quality and low-cost X-ray radiography.

Overall, all-inorganic CsPbX₃ nanocrystals have been demonstrated as potential candidates of scintillating materials for excellent X-ray scintillation and radiophotography with fast scintillation response, low detection limit, efficient multicolor radioluminescence and convenient solution-processability. Further developments of these promising nano-scintillator materials are also expected to be achieved in efficient and low-cost X-ray imaging areas.

* Corresponding author.

E-mail address: ruizhangh@163.com (H. Zhang).




Fig. 1. Scintillation performance of CsPbBr₃ PNCs scintillators. (a) Low-resolution TEM image of CsPbBr₃ nanocrystals with the inset high-resolution TEM image of a single CsPbBr₃ nanocrystal. (b) CsPbX₃ (X = Cl, Br, I) nanocrystals with tunable emission wavelength. (c) Comparison of scintillation ability of different scintillator materials. (d) Measured radioluminescence decay of CsPbBr₃ scintillator excited by 661 keV photons from ¹³⁷Cs source. (e) Design of X-ray panels with perovskite nanocrystal film. (f) X-ray images of α -Si photodiode panel acquired with the CsPbBr₃ nanocrystal scintillators. Reprinted with permission from Ref. [7]. Copyright 2018 Nature/Springer/Palgrave.

Conflict of interest

The authors declare that they have no conflict of interest.

References

- [1] Blasse G. Scintillator materials. *Chem Mater* 1994;6:1465–75.
- [2] Zhang X, Guo Z, Liu J, et al. Near infrared light triggered nitric oxide releasing platform based on upconversion nanoparticles for synergistic therapy of cancer stem-like cells. *Sci Bull* 2017;62:985–96.
- [3] Nikl M, Yoshikawa A. Recent R&D trends in inorganic single-crystal scintillator materials for radiation detection. *Adv Opt Mater* 2015;3:463–81.
- [4] Fu P, Shan Q, Shang Y, et al. Perovskite nanocrystals: synthesis, properties and applications. *Sci Bull* 2017;62:369–80.
- [5] Birowosuto MD, Cortecchia D, Drozdowski W, et al. X-ray scintillation in lead halide perovskite crystals. *Sci Rep* 2016;6:37254.
- [6] Xie A, Nguyen TH, Hettiarachchi C, et al. Thermal quenching and dose studies of X-ray luminescence in single crystals of halide perovskites. *J Phys Chem C* 2018;122:16265–73.
- [7] Chen Q, Wu J, Ou X, et al. All-inorganic perovskite nanocrystal scintillators. *Nature* 2018;561:88–93.
- [8] Chen W. Nanoparticle fluorescence based technology for biological applications. *J Nanosci Nanotechnol* 2008;8:1019–51.
- [9] Heo JH, Shin DH, Park JK, et al. High-performance next-generation perovskite nanocrystal scintillator for nondestructive X-ray imaging. *Adv Mater* 2018;30:1801743–49.
- [10] Zhang Y, Sun R, Ou X, et al. Metal halide perovskite nanosheet for X-ray high-resolution scintillation imaging screens. *ACS Nano* 2019;13:2520–5.



Kang Wang received his B.S. degree in 2013 at Shandong University, and Ph.D. degree in 2018 at Peking University. He joined the Aerospace Institute of Advanced Materials & Processing Technology in 2018. His current research focuses on nanomaterial synthesis and aerospace composite materials.



Hao Zhang received his B.S. degree in 2002 at University of Science and Technology of China, and Ph.D. degree in 2007 at Institute of Chemistry, Chinese Academy of Sciences. Now, he is the Deputy Director of Aerospace Institute of Advanced Materials & Processing Technology. His research interests include aerospace composites and nanomaterials.

All-inorganic perovskite nanocrystal materials: new generation of scintillators for high quality X-ray imaging

[Kang Wang](#), [Hao Zhang](#) and [Zhanjun Gu](#)

Citation: [Science Bulletin](#) **64**, 1205 (2019); doi: 10.1016/j.scib.2019.07.009

View online: <http://engine.scichina.com/doi/10.1016/j.scib.2019.07.009>

View Table of Contents: <http://engine.scichina.com/publisher/scp/journal/SB/64/17>

Published by the [Science China Press](#)

Articles you may be interested in

[Ligand density control boosts the efficiency of all-inorganic CsPbBr₃ perovskite nanocrystal based light emitting diodes](#)

[Science Bulletin](#) **62**, 314 (2017);

[A two-terminal all-inorganic perovskite/organic tandem solar cell](#)

[Science Bulletin](#) **64**, 885 (2019);

[Constructing robust all-inorganic contacts enable stable perovskite solar cells with efficiencies over 20%](#)

[SCIENCE CHINA Materials](#) **61**, 125 (2018);

[Radiation properties of high-order harmonic generation for the measurements of femto- and attosecond X-ray pulses](#)

[Chinese Science Bulletin](#) **54**, 2205 (2009);

[X-ray scintillation in lead-free double perovskite crystals](#)

[SCIENCE CHINA Chemistry](#) **61**, 1581 (2018);

